## **PCT**

# WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



### INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 4:	A1	11) International Publication Number: WO 86/00533	
A61L 27/00		(43) International Publication Date: 30 January 1986 (30.01.86)	
(21) International Application Number: PCT/NL (22) International Filing Date: 10 July 1985 (		reaux, Nieuwe Parklaan 107, NL-2587 BP The Hagus	
(31) Priority Application Number: (32) Priority Date: 10 July 1984 ( (33) Priority Country:	84021 (10.07.8	ropean patent), BR, CH (European patent), DE (European patent), DK, FI, FR (European patent), GI (European patent), IT (European patent), JP, LU	
(71) Applicant (for all designated States except US SUNIVERSITEIT TE GRONINGEN [NL/1] erstraat 5, NL-9712 PC Groningen (NL).  (72) Inventors; and (75) Inventors/Applicants (for US only): LEENSL Willem [NL/NL]; De Einthovenlaan 29, NL Doetinchem (NL). PENNINGS, Albert, John NL]; Ettenlaan 3, NL-9331 BE Norg (NL). René, Pieter, Hendrick [NL/NL]; De Wilgen 9781 ME Bedum (NL). JANSEN, Henricus, Bernhard [NL/NL]; Verweylaan 14, NL-9 Haren (NL).	AG, Ja-7002 F han [N ). VET 2-4, N Wilhel	Published  With international search report.	

### (57) Abstract

An implant article for treatment in reconstructive surgery of damage caused to bony material, said article comprising a composite of fibre material which may or may not be bio-degradable and is incorporated in a porous matrix of a bio-degradable organic polymer material.



## FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GA	Gabon	MR	Mauritania
ΑU	Australia	GB	United Kingdom	MW	Malawi
RB	Barbados	HU	Hunsary	NI.	Netherlands
BE	Belgium	IT	Italy	NO	Norway
BG	Bulenria	JР	Japan	RO	Romania
BR	8mzil	KP	Democratic People's Republic	SD	Sudan
CF.	Central African Republic		of Korea	SE	Sweden
CG	Conso	KR	Republic of Korea	SN	Senegal
CH	Switzertand	Ll	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanta	TD	Chad
DE	Germany, Federal Republic of	LU	Luxembourg	TG	Тово
DX	Denmark	MC	Monaco	US	United States of America
FI	Finland	MG	Madagascar		
FR	France	ML	Mati		



WO 86/00533 PCT/NL85/00027

-1-

Title:

Bone implant.

The present invention relates to an implent article for treatment in reconstructive surgery of damage caused to bony material.

At present it is being recognised that the meniscus is an important component of the knee-joint in case of injuries the repair or preservation of the undamaged part of which is preferred over the surgical removal of the meniscus. In this connection experience has shown that a damaged, e.g. torn, meniscus can only be healed if vascularisation of the injury is possible. It has further been established with animals by way of experiment that by reconstructive surgery of wedge-shaped and longitudinal injuries of the meniscus healing is effected by means of a synovial flap and after implantation of an implant article consisting of carbon fibres (Clin. Orthop. 181 (1983) 250-254). Although implantation of carbon fibres has proved to be a promising method of treating damaged menisci, technical deficiencies have become apparent, in most cases relating to a tendency to dislocation of the bundle of carbon fibres.

It is an object of the present invention to provide an implant article giving a solution for the above-mentioned drawback and permitting a more rapid ingrowth of tissue and vessels.

According to the present invention there is provided for this purpose an implant article of the above-mentioned type which is characterised by a composite of fibre material which may or may not be bio-degradable and is incorporated in a porous matrix of a bio25 degradable organic polymer material.

10

15

20

25

The bio-degradable organic polymer material used for the matrix may be a polyurethane material, e.g., a polyether urcthane, a polyester urethane and a polyether urea urethane; a polylactide material, e.g., a poly(L-lactide), a poly(D-lactide) and a poly(D,L-lactide); a polyglycolide material, e.g., a polyglycolide acid and copolymers composed of the different lactide materials, glycolide materials and other hydroxycarboxylic acids, as well as homopolymers and copolymers of amino acids. The individual polymer materials of mixtures thereof may be used, if required, with other bio-degradable polymer materials, e.g., with a porous polyamide material.

The fibre material for reinforcing the composite according to the invention may be incorporated in the matrix as loose fibres, however, also as a woven fabric, a knitted fabric or another coherent combination of fibres. The fibres to be used according to the invention may or may not be bio-degradable and comprise, e.g., carbon fibres; sufficiently strong polyethylene fibres; poly(L-lactide fibres), if required, with additives, e.g., low-molecular additives or bio-degradable homopolymers and/or copolymers; polyglycolide fibres; polyaramide fibres, e.g., poly(p-aminobenzoic acid) fibres; polyamide fibres, e.g., nylon fibres, or fibres of glycolide lactide copolymers.

The composite according to the invention may also include, e.g., materials capable of accelerating the bio-degradability of the matrix and the bio-degradability of the fibres, promoting ingrowth of tissue, having antibacterial activity and/or analgetic activity. Examples of such materials are citric acid, sodium citrate, salicylic acid, aspirin, tartaric acid, magnesium chloride and calcium phosphate.

It has turned out that the composite according to the invention is a product which, in addition to bio-degradable and bio-compatible properties, is also microporous and is therefore eminently suitable for effecting vascularisation or ingrowth of tissue, without which properties the repair of torn bone material, such as cartilage material of the meniscus, must be ruled out. By embedding the reinforcing fibre material according to the invention in a matrix of a bio-degradable organic polymer material, no shift of the fibres appears to occur during the healing process.

Although the properties of the composite according to the invention have been elucidated above, especially by means of the reconstructive-surgical treatment of meniscus injuries, the use of the composite is not restricted thereto.

A composite according to the invention useful in practice

15 for the repair of large wedge=shaped tears of the meniscus in dogs

has appeared to be an implant article made of a polyurethane-poly(L-lactide)

organic polymer material as the matrix, in combination with carbon

fibres. The composite formed therefrom was bio-degradable and bio-compatible

and further microporous.

20 The invention is illustrated by the following example.

#### Example

A. The materials used in this example for the preparation of the composite.

There was used a segmented poly(ether urethane) commercially 25 available under the trade name Estane 5714F1 (Goodrich, Co., Breckville, Ohio, U.S.A.).

Ť

7.7

5

20

25

The polylactide used was poly(L-lactide)  $(\overline{M}_v = 3.5 \times 10^5)$ , synthesised according to a process disclosed in the literature (Polymer 23 (1982) 1587).

To reinforcing material used was commercially available carbon fibres (Grafil EAS) (Courtaulds, Ltd., Coventry, England).

Sodium citrate (Merck) was further added to the subsequently prepared polymer solutions, in a low concentration.

B. The preparation of the polymer solutions and the carbon fibres.

The polyurethane was reprecipitated 5 times (3 times from N,N-dimethylformamide (DMF), then 1 time from tetrahydrofuran (TMF) and finally, 1 more time from DMF). The precipitant used was demineralised water. Reprecipitation was carried out at room temperature. The precipitated polyurethane was washed with ethanol (96%), and air dried for 1 night, then dried in a vacuum stove for 1 more hour at T = 50°C.

Separate poly(L-lactide) - and polyurethane solutions were prepared which were added to each other just before each use. The solvent used for both polymers was a mixture of DMF and THF (DMF:THF = 75:25%  $^{V}/v$ ). The poly(L-lactide) solution was saturated with sodium citrate.

The total polymer concentration of the final solution was 4% /v; both polymers were mixed in a ratio of polyurethane:poly(L-lactide)=80:20%  $^{W}$ /w.

The composite involved in the in vivo examination was prepared from a 4% W/v solution. (For uses requiring larger pores this could be achieved by further diluting the polymer solutions.

A dilution of, e.g., 4% W/v, for instance, gave an average pore size of

 $\pm$  100 /um, and a dilution of 3%  $^{\rm W}/{\rm v}$  gave an average pore size of  $\pm$  250 /um).

The carbon fibres were extracted with an acetone-THF mixture (acetone:THF = 50:50%  $^{V}/v$ ) for 24 hours at room temperature and then air dried. Subsequently, the fibres were cut to the desired length.

- C. Preparation of the porous polymer sheets.
- 1. Without carbon fibres.
- (a) A tube provided with a Teflon layer was kept in the final polymer solution for 4 seconds (T = 20°C),
- (b) Then the tube was air dried for 15-20 seconds, with a rotary movement being performed.
  - (c) Subsequently the tube was immersed in a non-solvent (water, T = 45°C); residence time 2-3 minutes.
- (d) Then the tube was placed in cold water (T = 10°C, residence time 2 minutes) and subsequently in ethanol (96%), (residence time: 2 minutes); finally, the tube was immersed in water (T = 20°C, residence time: 3 minutes).
  - (e) After that the outermost polymer layer was carefully dried with blotting-paper. Thus one porous polymer layer was obtained.
- This operation was repeated until a porous polymer sheet was obtained having the desired thickness and without carbon fibres.
  - 2. With carbon fibres.
- (a) For a method of preparing a porous polymer sheet with carbon fibros 10 layers of the polymer were applied to the tube in the manner as described above.
  - (b) Then the carbon fibres (2 layers, crosswise arranged over each other) were affixed to the tube and the immersing/coating process was continued with another 10 polymer layers.

According to another method carbon fibres were disposed in a layer of polymer solution (2 layers, crosswise arranged over each other), after which the non-solvent (water,  $T=45\,^{\circ}\text{C}$ ) was added with an atomizer. After the above-described treatment the whole was repeated for 4 more times. Then the carbon fibres were sufficiently fastened in the polymer matrix to continue the immersing/coating process with this fabric (see C. (a)-(e)), with the composition being effected on both sides.

The final composite was built up of layers of the porous sheets

as obtained under C., the polymer sheets with and without carbon fibres

being alternately processed in the final composite. The different

layers were bonded together with a 1% "/v polymer solution, using the

process mentioned under C. Thus the composite was brought to the required

dimensions from which the final meniscus prosthesis could be cut to

size.

It is noted that, in addition to the above-mentioned mixture DMF/THF 75:25% V/v, e.g., also DMF/1.4-dioxane mixtures (75-25% V/v) (or other ratios) may be used. The resulting materials thereby obtain a somewhat different porous structure which may be very suited for orthopedic uses. Suitable solvents are further dimethylacetamide and dimethylsulfoxide.

In the above-indicated manner and with the indicated starting materials a composite was prepared on the basis of a mixture composed of 95 wt.% polyurethane and 5 wt.% poly(L-lactide), using the process described under C.2. (a). The resulting composite was microporous with a pore size of 35-50 /um.

WO 86/00533 PCT/NL85/00027

-7-

5

with the composite a research into the chances of a torn
meniscus to be healed was conducted with a group of 12 dogs. Of each of the
dogs a meniscus was surgically provided with a large wedge-shaped
incision extending over approximately 30% of the meniscus.

For the repair of the menisci the composite was folded double and sewed together, then adapted to the actual size of the damaged meniscus to be treated, placed in the incision and sewed together therein with 3-0 Dexon sewing-thread. The wound was closed and the dogs were given an opportunity to get on their legs again as soon as possible.

process was evaluated arthroscopically, morphologically and histologically in the manner appropriate therefor from a medical point of view.

It turned out that all the implant elements except one had remained in position, and that ingrowth of fibrous fibro-cartilaginous material had taken place over a substantial distance from the place where the implant element is in contact with the surrounding meniscus.

In two cases the meniscus proved to have healed already completely.

After a period of 14-19 weeks the implant element proved to have been completely absorbed in the meniscus.

In a combination of a wedge-shaped and a longitudinal tear in the meniscus of rabbits, application of the implant element to these injuries of the meniscus proved to induce nearly complete healing.

Summarizing, the composite according to the invention proves

25 to be easy in handling owing to applying the organic polymer matrix

and conducive to ingrowth of tissue and vessels because of the micro-

porous condition thereof. These last-mentioned properties are necessary

for enabling a damaged meniscus to heal, as appears from

S.S. Arnockzy et al., "The microvasculature of the meniscus and its
response to surgery", Am.J. Sports med. 11 (1983) 131;

R.P.H. Veth et al., Clin. Orthop. 175 (1983) 259 and Clin.Orthop. 181
(1983) 212.

### CLAIMS

- 1. An implant article for treatment in reconstructive surgery of damage caused to bony material, characterised by a composite of fibre material which may or may not be bio-degradable and is incorporated in a porous matrix of a bio-degradable organic polymer material.
- 2. An implant article according to claim 1, characterised in that the bio-degradable organic polymer material is a polyurethane, a polylactide, a polyglycolide, a polyamide, a polyester and/or a copoly (<-amino acid) material.
- 3. An implant article according to claim 2, characterised in that
  10 the polyurethane material is a polyether urethane, a polyester urethane
  and/or a polyether urea urethane.
  - 4. An implant article according to claim 2, characterised in that the polylactide material is a poly(L-lactide), a poly(D-lactide) and/or a poly(D,L-lactide).
- 15 5. An implant article according to claim 2, characterised in that the polyglycolide material is polyglycolic acid.
  - 6. An implant article according to claim 2, characterised in that the polyamide material is a porous polyamide.
- 7. An implant article according to claim 1, characterised in
  20 that it contains the fibre material as loose fibres and/or as a coherent
  combination of fibres and that the employable fibre material is carbon
  fibres, polyethylene fibres, poly(L-lactide) fibres, polyglycolide fibres,
  polyaramide fibres, polyamide fibres and/or fibres of glycolide-lactide
  copolymers, as well as fibres of other poly(X-hydroxycarboxylic acids),

- a poly( $\Lambda$ -methylpropiolactone), poly(dioxanone), polyglycine and other poly( $\Lambda$ -amino acids), polypropylene and polyesters.
- 8. An implant article according to claim 7, characterised in that the poly(L-lactide) fibres contain low-molecular additives and/or bio-degradable homopolymers and/or copolymers.
- 9. An implant article according to claim 1, characterised in that the organic material is prepared from a mixture of a polyurethane, a poly(L-lactide) and a polyamide in different ratios.
- 10. An implant article according to claim 9, characterised in

  10 that the organic material is prepared from approximately 80-95% polyurethane and 20-5% poly(L-lactide).

# INTERNATIONAL SEARCH REPORT

International Application No PCT/NL 85/00027

I. CLAS	SSIFICATION OF SUBJECT MATTER (it several cla	saification sympols apply, indicate any t		
	ing to thremshall Patent Classification (IPC) or to both h	Vetional Classification and IPC		
IPC4:	A 61 L 27/00			
D. PIEL	DS SEARCHED			
Cleanifica	Minimum Occun	nentation Searched ?		
	Jereni	Classification Symbols	2 And 1 Control of the Control of th	
IPG,	A 61 L			
	Documentation Searched other	r than Minimum Occumentation		
	to the Extent that such Documen	its are included in the Fields Searched *		
Category *	MENTS CONSIDERED TO BE RELEVANT			
- Aldford	Citation of Occument, 11 with Indication, where so	propriate, of the relevant passages 13	Relevant to Claim No. 13	
X	US. A 4411027 (H ALEVAN	DED -+ -3 1 05		
••	US, A, 4411027 (H. ALEXANI ber 1983, see column	DER et al.) 25 Octo-		
	column 4, lines 1,2	5, IInes 66-68;	1,5	
Y	,		2,3,6,7,10	
		İ	2,3,0,7,10	
X	EP, A, 0011528 (INSERM) 28	8 May 1980,		
.,	see pages 2,3		1,4	
Y			2,7	
v	FR & 2350926 (Dammerre			
.	FR, A, 2350826 (BATTELLE-1 1977, see page 3, line	INSTITUT) 9 December	_	
	acc bade 1, TIME	s I-II; Claims 2,14	2	
Y	FR, A, 2387028 (UNION CARE	BIDE) 10 November		
[	19/8, see page 12, lin	ies 17-27; page 21.	2,6	
ļ	lines 27-32		-,-	
Y	IIS D 3463158 /F F 60000			
-	US, A, 3463158 (E.E. SCHMI	TT et al.) 26	_	
ļ	August 1969, see colum	n 2, lines 24-40;	7	
į		į		
Y	FR, A, 2364644 (INSERM) 20	September 1976		
ĺ	see page 6		7	
i		; }	1	
• Special	categories of cited documents; 10			
"A" docu.	ment defining the general state of the art which is not dered to be of particular relevance	"I" later document published after the or prienty date and not in conflict	international filing date	
	document but nublished as or sheet the	invention	ir treory underlying the	
"L" docu	Dent which may then you	"X" document of particular relevance: cannot be considered novel or ca involve an inventive stee	the claimed invention	
Crtaire	in or differ special tesson for another	"Y" document of particular relevance		
woob "O" watto	fient referring to an oral disclosure, use, exhibition or means	document is completed by this are	to sett med when the	
"P" docur	nent published prior to the international filing date but han the priority date elarned	in the art.	ous to a person smiled	
	, iy training	document member of the same part	Int lamily	
ate of the Actual Completion of the				
15th October 1985				
1 4 NOV. 1880 /				
	Searching Authority	Signature of Authorized Officer	11 00 000	
1	EUROPEAN PATENT OFFICE	(	Mully	
PCT//SA/210 (second second sec				

Form PCT/ISA/210 (second sheet) (January 1985)

	1	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No
alegory *		Original or exemitatic and underline and a spinories or na testion becoming	Maistern to Crant No
¥	EP,	A, 0050215 (AMERICAN CYANAMID) 28 April 1982, see page 4, line 3	7
Y	WO,	A, 84/00302 (RIJKSUNIVERSITEIT TE GRONING- EN) 2 Februar 1984, see page 3, lines 25- 32	3,10
A	us,	A, 3739773 (AMERICAN CYANAMID) 19 June 1973, see column 5, lines 64-66	
		·	
		,	
j			

## ANNEX TO THE INTERNATIONAL SEARCH REPORT ON

INTERNATIONAL APPLICATION NO. PCT/NL 85/00027 (SA 10115)

This Annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on 08/11/85

The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent f member		Publication date
US-A- 4411027	25/10/83	US-A- 4329743 CA-A- 1158806 US-A- 4512038		18/05/82 20/12/83 23/04/85
EP-A- 0011528	28/05/80	FR-A,B US-A-	2439003 4279249	16/05/80 21/07/81
FR-A- 2350826	09/12/77	NL=A= DE=A,B AT=B= GB=A= US=A= CH=A= DE=A,B	7704659 2620891 352867 1562758 4192021 632158 2620890	15/11/77 17/11/77 10/10/79 19/03/80 11/03/80 30/09/82 17/11/77
FR-A= 2387028	10/11/78	DE-A,C US-A- JP-A- CH-A- GB-A- CA-A- US-A-	2816072 4164794 53128191 621059 1602932 1138153 4362681	19/10/78 21/08/79 08/11/78 15/01/81 18/11/81 28/12/82 07/12/82
US-A- 3463158	26/08/69	CH-A- GB-A- DE-A,C CA-A-	495755 1217601 1667932 943735	15/09/70 31/12/70 18/05/72 19/03/74
FR-A- 2364644	14/04/78	NL-A- BE-A- DE-A- GB-A- CH-A-	7710315 858815 2742128 1593288 624572	22/03/78 16/03/78 23/03/78 15/07/81 14/08/81
EP-A- 0050215	28/04/82	JP-A- US-A-	57098556 4496446	18/06/82 29/01/85
WO-A- 8400301	02/02/84	NL-A- AU-A- EP-A-	8202893 1710083 0118458	16/02/84 08/02/84 19/09/84

For more details about this annex :

see Official Journal of the European Patent Office, No. 12/82

INTERNATIONAL APPLICATION NO.

PCT/NL 85/00027 (SA 10115)

US-A- 3739773 19/06/73 US-A- 3875937 08/04/75 US-A- 3620218 16/11/71 BE-A- 654236 09/04/65